



# Ultraleather® | Pony



Truly one-of-a-kind, the handsome intrigue of **Ultraleather® | Pony** conjures up the soft gleam of a well-brushed hide. Its subtle texture realistically captures the look of genuine horsehair. Dual-color layers are skillfully combined to create an authentic, dimensional texture, resulting in an ideal statement for wallcovering and upholstery applications.

#### Distinctive Characteristics:

- Superior durability – industry-leading 14+ weeks hydrolysis results
- Blended backcloth for expanded upholstery capabilities
- 400,000 double rubs (Wyzenbeek), 180,000 rubs (Martindale)
- Bleach cleanable (1:5 bleach/water solution)
- SCS Indoor Advantage Gold Certification
- Meets Health Care Without Harm's Healthy Interiors Criteria V2.3

Providing hard-working upholstery solutions – the Ultraleather® family redefines performance fabrics with classic aesthetics and authentic softness.

# Ultraleather® | Pony

---

## General Specifications

### Composition:

100% Polycarbonate Polyurethane Surface  
65% Polyester, 35% Rayon Backing

### Weight:

Approx. 11.8 oz. Per Square Yard  
Approx. 400 Grams Per Square Metre

### Thickness:

Approx. 1.15 Millimetres

### Width:

54 Inches / 137 Centimetres

### Repeat:

4"V x 4"H / 102mm V x 102mm H

## Performance

### Abrasion:

ASTM D4157 / 400,000 Double Rubs (Wyzenbeek)\*  
BS EN ISO 12947-2 / 180,000 Rubs (Martindale)\*

\*meets or exceeds

### Hydrolysis:

14+ Weeks  
ASTM D3690 Sect. 6.11 (Hydrolytic Stability)  
ISO 1419 Method C (Accelerated Ageing)

Adhesion of Coating: ASTM D751

Tear Strength: ASTM D2261

Breaking Strength: ASTM D5034

Tensile Strength: BS EN ISO 1421

## Colorfastness

### Light Fastness:

AATCC 16.3, 200 Hours, Grade 4  
ISO 105 B02, Grade 6

### Crocking:

AATCC 8, Grade 4-5 Wet & Dry

## Flammability Requirements

- ASTM E84 (Adhered) - Class A
- CA TB 117 - Pass
- FMVSS 302 & 95/28 Annex IV - Pass
- NFPA 260 - Class 1
- UFAC - Class 1

These fabrics, when treated and/or used with other compatible furniture components, have been shown to perform under the fire test conditions of:

- ASTM E84 (Unadhered)
- BS 5852 Source 0, 1 & 5 (Cig, Match & Crib 5)
- BS 5867 Part 2 Type B
- BS 7175
- FAR Specifications
- IMO Part 8
- NFPA 701

For more information on certifications and standards, sustainability, as well as cleaning and care instructions, please visit our website.

